

Rilsan® Clear **G830 Rnew** is a high performance transparent polyamide partially based on renewable resources. This grade has been specially designed for injection molding applications, ideally suited for optics as high end eyewear frames.

GENERAL PROPERTIES	METHOD	UNIT	TYPICAL VALUES
Percentage of renewable carbon	ASTM 6866	%	53-55
Density	ISO R 1183 D	g/cm ³	1.01
Water absorption at equilibrium at 23°C and 50 % RH	ISO 62	%	1.3
Water absorption at equilibrium at 23°C in water		%	3.3
Glass transition temperature (Tg)	ISO 11357	°C	135
Heat deflection temperature (HDT) under 0.45 MPa under 1.8 MPa	ISO 75	°C	110
		°C	95
Transparency (560 nm, 2mm)	ISO 13168-1,2	%	91.5
Shrinkage (after 24h, 2 mm, mould at 40°C) // ⊥	Internal method	%	0.1
		%	0.5
Hardness shore (*) instantaneous after 15 s	ISO 868	Shore D	83
		Shore D	81
Tensile test (*) stress at yield strain at yield stress at break strain at break	ISO 527	MPa	55
		%	7
		MPa	60
		%	> 150
Tensile modulus (*)	ISO 527	MPa	1690
Flexural modulus (*)	ISO 178	MPa	1530
Charpy impact unnotched 23°C unnotched -30°C notched 23°C notched -30°C	ISO 179/1eU " ISO 179/1eA "	kJ/m ² " " "	No break No break 11 10

(*) Samples conditioned 15 days, 23°C - 50 % R.H.

PROCESSING CONDITIONS	TYPICAL VALUES
Drying (*): time / temperature	4-6 hours / 70-80°C
Injection temperature: min / recommended / max	240°C / 270°C / 300°C
Mold temperature:	20-80°C

(*) Rilsan® Clear is delivered dried in sealed packaging ready to be processed. Drying is only necessary for bags opened for more than 2 hours.

DPT/TDS/057290/October 2009

The information contained in this document is based on trials carried out by our Research Centres and data selected from the literature, but shall in no event be held to constitute or imply any warranty, undertaking, express or implied commitment from our part. Our formal specifications define the limit of our commitment. No liability whatsoever can be accepted by Arkema with regard to the handling, processing or use of the product or products concerned which must in all cases be employed in accordance with all relevant laws and/or regulations in force in the country or countries concerned.